



The Glue People
Trade Grade Products Ltd
 Unit 2, Thorne Way
 Woolsbridge Industrial Park
 Three Legged Cross
 Wimborne, Dorset, BH21 6FB

Tel 01202 820177
 Fax 01202 814011

Tradeseal MS/HG

High quality MS-Polymer adhesive

Product Description

Tradeseal MS/HG is a high quality, single component, high strength adhesive. It is based on MS-Polymer, chemically neutral and fully elastic. Tradeseal MS/HG is formulated as a High Grab, safe to use, general purpose adhesive for use in many industries.

Characteristics

- Safe to use - No isocyanates, halogens, acids, alkalis or solvents.
- Minimal health and safety considerations.
- High bond strength on nearly all surfaces.
- Very high grab – most materials will need no support during cure.
- Highly resistant to all weathers, sea water, etc
- Excellent adhesion on porous surfaces and most plastics, including PVC and GRP.
- High performance mechanical properties.
- Flexible elastic rubber – movement accommodation up to 25%.
- Straightforward application even in adverse conditions.
- No bubble formation within sealant (in high temperature and humidity applications).
- Primerless adhesion (except where capillary water pressure can occur).
- Very easy to tool and finish.
- Colour stability and UV resistant – does not yellow.
- Ecological advantages – free of isocyanates, solvents, halogens and acids.
- Over-paintable with all water based paints and many other systems.
- Resistant to many chemicals.
- No staining of porous materials such as natural stone, granite (for marble please test a small area first).

Applications

- All bonding applications in the building and metal industry
- Structural bonding in vibration constructions
- Panel bonding for caravans and commercial vehicles.
- Many bonding applications in the marine industry.

Packaging and Colours

Colours:	White – Black
Packaging:	Thick wall cartridge of 290 ML

Shelflife

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Technical Data

Base:	Hybrid polymer
Consistency:	Stable Paste
Curing System:	Moisture Cure
Skin Formation:	10 min (20°C/65% relative humidity)
Curing Rate:	2-3mm/24h (20°C/65% R.H.)
Hardness:	50 ± 5 Shore A
Shrink:	None
Specific Gravity:	1.62
Temperature Resistance:	-40°C until +90°C
Elongated at break:	500% (DIN 53504)
Elasticity Modulus 100%:	1.3 N/mm ² (DIN 53504)
Breaking Strength:	2.0 N/mm ² (DIN 53504)
Elastical recovery:	>70%
Max Allowed Distortion:	20% ±

Chemical resistance

Good:	Poor:
Water, inc sea water.	Aromatic solvents
Aliphatic solvents	Concentrated acids
Mineral oils	Chlorinated hydrogen
Grease	
Diluted inorganic acids and alkalis	

Application

Surface preparation:	Clean, dry and free from dust, grease and any other contaminants. Non porous surfaces may be primed with TGP Surface Activator.
Application method:	Manual or pneumatic caulking gun
Application temperature:	+1°C until +30°C
Cleaning:	Clean with white spirits immediately after application
Finishing:	Smooth joint with a soapy solution before skin forming

Transport Information

Road:	ADR	Free
Maritime:	IMDG	Free
Air:	ICAO / IATA-DGR	Free
UN Number:	None	Does not apply

Labelling

No hazardous labelling required.

Information

Tradeseal MS may be overpainted, however, due to the large number of paints and varnishes available we strongly recommend a compatibility test prior to application. The drying time of alkyd resin paints may increase.

Important Notice

Data contained in this document is for information only and is believed to be reliable. Trade Grade Products Ltd (TGP) cannot assume responsibility for results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability of the product for any specific purpose and TGP is pleased to provide a sample upon request.

Before using this product ensure that you have been supplied with and have read carefully the following information.

- The hazard label (complying with latest CDG/CPL regulations) applied to the container.
- Material Safety Data Sheet, Tradeseal MS/HG.